

MOTIVE T875-AGM

MODEL T875-AGM

VOLTAGE 8

CAPACITY 160Ah @ 20Hr MATERIAL Polypropylene

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required







8 VOLT

PHYSICAL SPECIFICATIONS

| BCI | MODEL NAME | TERMINAL TYPE | DIMENSIONS [©] INCHES (mm) | | WEIGHT LBS. (kg) | HANDLES | INSTALLATION ORIENTATION | |
|-----|------------|---------------|-------------------------------------|------------|------------------|---------|--------------------------|----------------------------|
| 000 | T875-AGM | M8/AP/LT | LENGTH | WIDTH | HEIGHTF | () | Embedded | Horizontal and Vertical |
| GC8 | | | 10.30 (262) | 7.06 (179) | 10.73 (273) | 70 (32) | | |

ELECTRICAL SPECIFICATIONS

| VOLTAGE | CRANKING PERFORMANCE | | CAPACITY A MINUTES | | CAPACITY ^B AMP-HOURS (Ah) | | | 1) | ENERGY (kWh) | INTERNAL RESISTANCE (mΩ) | SHORT CIRCUIT CURRENT (amps) |
|---------|--------------------------|-------------------------|--------------------|-----------|--------------------------------------|-------|-------|--------|--------------|--------------------------|------------------------------|
| 0 | C.C.A. ^D @0°F | C.A. ^E @32°F | @ 25 Amps | @ 56 Amps | 5-Hr | 10-Hr | 20-Hr | 100-Hr | 100-Hr | 3.0 2780 | 2700 |
| 0 | _ | _ | 320 | 118 | 130 | 142 | 160 | 170 | 1.36 | 3.0 | 2/80 |

CHARGING INSTRUCTIONS

| CHARGER VOLTAGE SETTINGS (AT 77°F/25°C) | | | | |
|---|------------------------|-------|-------|--|
| SYSTEM VOLTAGE | 8V | 24V | 48V | |
| Maximum Charge Current (A) | 20% of C ₂₀ | | | |
| Absorption Voltage (2.40 V/cell) | 9.60 | 28.80 | 57.60 | |
| Float Voltage (2.25 V/cell) | 9.00 | 27.00 | 54.00 | |

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

| ADD | SUBTRACT |
|--|--|
| 0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F | 0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F |

OPERATIONAL DATA

| OPERATING TEMPERATURE | SELF DISCHARGE | | |
|---|--|--|--|
| -4°F to 122°F (-20°C to +50°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%. | Less than 3% per month depending on storage temperature conditions | | |

RECYCLE RESPONSIBLY









STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

| PERCENTAGE CHARGE | CELL | 8 VOLT |
|-------------------|------|--------|
| 100 | 2.14 | 8.56 |
| 75 | 2.09 | 8.36 |
| 50 | 2.04 | 8.16 |
| 25 | 1.99 | 7.96 |
| 0 | 1.94 | 7.76 |


TROJAN T875-AGM PERFORMANCE





PERCENT CAPACITY VS. TEMPERATURE




BATTERY DIMENSIONS (shown with M8)








SELF DISCHARGE VS. TIME



TERMINAL TYPE^G



M8 WITH AP ADAPTER (ADAPTER PROVIDED BUT NOT INSTALLED) **Battery Height with Terminal in Inches (mm)** 11.41 (290) Torque Values in-lb (Nm) Connection to M8: 85 - 90 (10 - 11)Connection to AP: 50 - 70 (6 - 8)

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are
- The families of minutes a activity of an element when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.73 vicelic capacitic based on peak performance.

 The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
- Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.
- C.C.A. (Cold Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2
- CAL Clothaning Analysis the discharge lose than it amperes which a reversible to the analysis at 22 Victor. Widel. This is sometimes referred to ask an arian cranting amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.
- Batteries in storage should be charged when they decline to 75% State of Charge (SOC).
- Weight may vary.











Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

